



(12)

EUROPEAN PATENT SPECIFICATION

(45) Date of publication of patent specification :
06.05.92 Bulletin 92/19

(51) Int. Cl.⁵ : **B41M 5/38**

(21) Application number : **89117520.0**

(22) Date of filing : **22.09.89**

(54) **Thermally-transferable fluorescent diphenylpyrazolines.**

(30) Priority : 30.09.88 US 251263

(43) Date of publication of application :
09.05.90 Bulletin 90/19

(46) Publication of the grant of the patent :
06.05.92 Bulletin 92/19

(84) Designated Contracting States :
AT BE CH DE ES FR GB GR IT LI LU NL SE

(56) References cited :
EP-A- 0 279 330
EP-A- 0 279 467
PATENT ABSTRACTS OF JAPAN, vol. 12, no.
485 (M-777)[3332], 19th December 1988; JP-
A-63 205 288 (DAINIPPON PRINTING CO.)24-
08-1988

(73) Proprietor : **EASTMAN KODAK COMPANY**
343 State Street
Rochester, New York 14650-2201 (US)

(72) Inventor : **Byers, Gary Wayne c/o Eastman**
Kodak Company
Patent Department 343 State Street
Rochester New York 14650 (US)
Inventor : **Henzel, Richard Paul c/o Eastman**
Kodak Company
Patent Department 343 State Street
Rochester New York 14650 (US)

(74) Representative : **Brandes, Jürgen, Dr.Rer.Nat.**
et al
Wuesthoff & Wuesthoff, Patent- und
Rechtsanwälte, Schweigerstrasse 2
W-8000 München 90 (DE)

EP 0 366 923 B1

Note : Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid (Art. 99(1) European patent convention).

Description

This invention relates to fluorescent donor elements used in thermal transfer.


In recent years, thermal transfer systems have been developed to obtain prints from pictures which have been generated electronically from a color video camera. According to one way of obtaining such prints, an electronic picture is first subjected to color separation by color filters. The respective color-separated images are then converted into electrical signals. These signals are then operated on to produce cyan, magenta and yellow electrical signals. These signals are then transmitted to a thermal printer. To obtain the print, a cyan, magenta or yellow dye-donor element is placed face-to-face with a dye-receiving element. The two are then inserted between a thermal printing head and a platen roller. A line-type thermal printing head is used to apply heat from the back of the dye-donor sheet. The thermal printing head has many heating elements and is heated up sequentially in response to the cyan, magenta and yellow signals. The process is then repeated for the other two colors. A color hard copy is thus obtained which corresponds to the original picture viewed on a screen.

The system described above has been used to obtain visible dye images. However, for security purposes, to inhibit forgeries or duplication, or to encode confidential information, it would be advantageous to create non-visible ultraviolet absorbing images that fluoresce with visible emission when illuminated with ultraviolet light.

U.S. Patent 4,627,997 discloses a fluorescent thermal transfer recording medium comprising a thermally-meltable, wax ink layer. In that system, the fluorescent material is transferred along with the wax material when it is melted. Wax transfer systems, however, are incapable of providing a continuous tone. Further, the fluorescent materials of that reference are incapable of diffusing by themselves in the absence of the wax matrix. It is an object of this invention to provide fluorescent materials useful in a continuous tone system which have sufficient diffusivity to transfer by themselves from a donor element to a dye-receiver.

These and other objects are achieved in accordance with this invention which comprises a donor element for thermal transfer comprising a support having on one side thereof a fluorescent diphenylpyrazoline compound dispersed in a polymeric binder, and on the other side thereof a slipping layer comprising a lubricant.

In a preferred embodiment of the invention, the compound has the formula:



wherein:


R is hydrogen; cyano; carboxyalkyl; a substituted or unsubstituted alkyl group of 1 to 6 carbon atoms such as methyl, ethyl, methoxyethyl, or n-butyl;

or a substituted or unsubstituted aryl group of 6 to 10 carbon atoms such as $-C_6H_5$, $-C_6H_4(p-OCH_3)$, $-C_6H_4(o-CO_2CH_3)$, or $-C_6H_4(p-Cl)$;

J is hydrogen; a substituted or unsubstituted alkyl group of 1 to 6 carbon atoms such as those listed above for R; a substituted or unsubstituted aryl group of 6 to 10 carbon atoms such as those listed above for R; or may represent $-CH_2-$ or $-CH_2CH_2-$ to complete a 5- or 6-membered non-aromatic carbocyclic ring.

In a preferred embodiment of the invention, J is hydrogen. In another preferred embodiment, R is phenyl. The phenyl rings in the compounds described above may be substituted as long as such substitution does not interfere with the intended performance of the compounds.



Compounds included within the scope of the invention include the following:




Compound	R ¹	R ²	R ³	J
1	H	4-Cl	C ₆ H ₅	H
2	H	4-C ₆ H ₅	H	H
3	H	4(-O ₂ CCH ₃)	H	H
4	H	H	CN	H
5	H	3, 4(-OCH ₃)	H	H
6	4-CH ₃	H	H	H
7	4-CH ₃	H	CH ₃	-CH ₂ -
8	4-CH ₃	H	CH ₃	CH ₃
9	H	3, 4(-OCH ₃)	H	-C ₂ H ₄ -
10	4-Cl	4-Cl	H	-CH ₂ -
11	H	H	H	C ₆ H ₅

The above compounds may be made by reaction of the appropriate phenylhydrazine via the Knorr reaction: A.H. Corwin, "Heterocyclic Compounds," R. C. Elderfield, ed. Vol. 1, 1950, p. 287.

A visible dye can also be used in a separate area of the donor element of the invention provided it is transferable to the dye-receiving layer the action of heat. Especially good results have been obtained with sublimable dyes such as





(cyan)

or any of the dyes disclosed in U.S. Patent 4,541,830. The above dyes may be employed singly or in combination to obtain a monochrome. The dyes may be used at a coverage of from 0.05 to 1 g/m² and are preferably hydrophobic.

The fluorescent material in the donor element of the invention is dispersed in a polymeric binder such as a cellulose derivative, e.g., cellulose acetate hydrogen phthalate, cellulose acetate, cellulose acetate propionate, cellulose acetate butyrate, cellulose triacetate; a polycarbonate; poly(styrene-co-acrylonitrile), a poly(sulfone) or a poly(phenylene oxide). The binder may be used at a coverage of from 0.1 to 5 g/m².

The fluorescent material layer of the donor element may be coated on the support or printed thereon by a printing technique such as a gravure process.

Any material can be used as the support for the donor element of the invention provided it is dimensionally stable and can withstand the heat of the thermal printing heads. Such materials include polyesters such as poly(ethylene terephthalate); polyamides; polycarbonates; glassine paper; condenser paper; cellulose esters; fluorine polymers; polyethers; polyacetals; polyolefins; and polyimides. The support generally has a thickness of from 2 to 30 μ m. It may also be coated with a subbing layer, if desired.

The reverse side of the donor element is coated with a slipping layer to prevent the printing head from sticking to the donor element. Such a slipping layer would comprise a lubricating material such as a surface active agent, a liquid lubricant, a solid lubricant or mixtures thereof, with or without a polymeric binder. Preferred lubricating materials include oils or semi-crystalline organic solids that melt below 100°C such as any of those materials disclosed in U. S. Patents 4,717,711, 4,737,485, 4,738,950 and 4,717,712. Suitable polymeric binders for the slipping layer include poly(vinyl alcohol-co-butylal), poly(vinyl alcohol-co-acetal), poly(styrene), poly(vinyl acetate), cellulose acetate butyrate, cellulose acetate propionate, cellulose acetate or ethyl cellulose.

The amount of the lubricating material to be used in the slipping layer depends largely on the type of lubricating material, but is generally in the range of .001 to 2 g/m². If a polymeric binder is employed, the lubricating material is present in the range of 0.1 to 50 weight %, preferably 0.5 to 40, of the polymeric binder employed.

The receiving element that is used with the donor element of the invention usually comprises a support having thereon an image-receiving layer. The support may be a transparent film such as a poly(ether sulfone), a polyimide, a cellulose ester such as cellulose acetate, a poly(vinyl alcohol-co-acetal) or a poly(ethylene terephthalate). The support for the receiving element may also be reflective such as baryta-coated paper, polyethylene-coated paper, white polyester (polyester with white pigment incorporated therein), an ivory paper, a condenser paper or a synthetic paper such as duPont Tyvek®.

The image-receiving layer may comprise, for example, a polycarbonate, a polyurethane, a polyester polyvinyl chloride poly(styrene-co-acrylonitrile), poly(caprolactone) or mixtures thereof.

As noted above, the donor elements of the invention are used to form a transfer image. Such a process comprises imagewise-heating a donor element as described above and transferring a fluorescent material image to a receiving element to form the transfer image.

The donor element of the invention may be used in sheet form or in a continuous roll or ribbon. If a continuous roll or ribbon is employed, it may have only the fluorescent polycyclic-aromatic thereon as described above or may have alternating areas of different dyes, such as sublimable magenta and/or yellow and/or cyan and/or black or other dyes. Such dyes are disclosed in U. S. Patents 4,541,830; 4,698,651; 4,695,287; 4,701,439; 4,757,046; 4,743,582; and 4,753,922. Thus, one-, two-, three- or four-color elements for higher numbers also) are inclined within the scope of the invention.

In a preferred embodiment of the invention, the donor element comprises a poly(ethylene terephthalate) support coated with sequential repeating areas of magenta, yellow, and cyan dye and the fluorescent material as described above, and the above process steps are sequentially performed for each color to obtain a three-color dye transfer image containing a fluorescent image.

A thermal transfer assemblage of the invention comprises

a) a donor element as described above, and

b) a receiving element as described above, the receiving element being in a superposed relationship with the donor element so that the fluorescent material layer of the donor element is in contact with the image-receiving layer of the receiving element.

The following example is provided to illustrate the invention.

Example

A donor element was prepared by coating the following layers in the order recited on a 6 μm poly(ethylene terephthalate) support:

- 1) a subbing layer of duPont Tyzor TBT[®] titanium tetra-n-butoxide (0.16 g/m²) from 1-butanol; and
- 2) a layer containing the fluorescent material as identified above or control fluorescent material identified below (0.16 g/m²) in a cellulose acetate propionate (2.5% acetyl and 45% propionyl) binder (0.32 g/m²) coated from a cyclopentanone, toluene and methanol solvent mixture.


On the back side of the element was coated:

- 1) a subbing layer of Bostik 7650[®] (Emhart Corp.) polyester (0.11 g/m²) coated from toluene; and
- 2) a slipping layer of Gafac RA-600[®] (GAF Corp.) polymer (0.043 g/m²) and BYK-320[®] (BYK Chemie, USA) (0.016 g/m²) in a poly(styrene-co-acrylonitrile) binder (70:30 wt. ratio) (0.54 g/m²) coated from a toluene and 3-pentanone solvent mixture.

Control Materials


The following materials are available commercially from Kodak Laboratory products and Chemicals Division:

Control 1




Fluorescein

Control 2



Rhodamine B

Control 3



DANS Acid

A receiving element was prepared by coating a solution of Makrolon 5705[®] (Bayer A.G. Corporation) polycarbonate resin (2.9 g/m²) in a methylene chloride and trichloroethylene solvent mixture on a transparent 175 μm polyethylene terephthalate support.

The fluorescent material layer side of the donor element strip approximately 3 cm x 15 cm in area was placed in contact with the image-receiving layer of the receiver element of the same area. The assemblage was fastened in the jaws of a stepper motor driven pulling device. The assemblage was laid on top of a 14 mm diameter rubber roller and a TDK Thermal Head L-133 (No. 6-2R16-1) and was pressed with a spring at a force of 3.6 kg against the donor element side of the assemblage pushing it against the rubber roller.


The imaging electronics were activated causing the pulling device to draw the assemblage between the printing head and roller at 3.1 mm/sec. Coincidentally, the resistive elements in the thermal print head were pulsed at a per pixel pulse width of 8 msec to generate a graduated density image. The voltage supplied to the print head was approximately 25 v representing approximately 1.6 watts/dot (13 mjoules/dot).

The receiving element was separated from the donor element and the relative emission was evaluated with a spectrofluorimeter using a fixed intensity 360 nm excitation beam and measuring the relative area under the emission spectrum from 375 to 700 nm. The following results were obtained:

Table

<u>Compound</u>	<u>Relative Emission*</u>	<u>Visual Color</u>
None	7	Not visible
Comparison*	100	Blue
1	87	Blue
Control 1	<1	Not visible
Control 2	<1	Not visible
Control 3	<1	Not visible

* Compared to the following compound, normalized to 100:




The above results show that the compound of the invention has much more fluorescence than the control compounds of the prior art.

Claims

1. A donor element for thermal transfer comprising a support having on one side thereof a fluorescent diphenylpyrazoline compound dispersed in a polymeric binder, and on the other side thereof a slipping layer comprising a lubricant.

2. The element of Claim 1 characterized in that said compound has the formula:



wherein:

R is hydrogen; cyano; carboxyalkyl; a substituted or unsubstituted alkyl group of 1 to 6 carbon atoms; or a substituted or unsubstituted aryl group of 6 to 10 carbon atoms; and

J is hydrogen; a substituted or unsubstituted alkyl group of 1 to 6 carbon atoms; a substituted or unsubstituted aryl group of 6 to 10 carbon atoms; or may represent $-CH_2-$ or $-CH_2CH_2-$ to complete a 5- or 6-membered

non-aromatic carbocyclic ring.

3. The element of Claim 2 characterized in that J is hydrogen.

4. The element of Claim 2 characterized in that R is phenyl.

5. The element of Claim 1 characterized in that said donor element comprises sequential repeating areas of magenta, yellow and cyan dye, and said fluorescent compound.


6. A thermal transfer assemblage comprising:

a) a donor element comprising a support having on one side thereof a layer comprising a material dispersed in a polymeric binder, and on the other side thereof a slipping layer comprising a lubricant, and

b) a receiving element comprising a support having thereon an image-receiving layer,

said receiving element being in a superposed relationship with said donor element so that said material layer is in contact with said image-receiving layer, characterized in that said material is a fluorescent diphenyl-pyrazoline compound.

7. The assemblage of Claim 6 characterized in that said compound has the formula:



wherein:


R is hydrogen; cyano; carboxyalkyl; a substituted or unsubstituted alkyl group of 1 to 6 carbon atoms; or a substituted or unsubstituted aryl group of 6 to 10 carbon atoms; and

J is hydrogen; a substituted or unsubstituted alkyl group of 1 to 6 carbon atoms; a substituted or unsubstituted aryl group of 6 to 10 carbon atoms; or may represent $-CH_2-$ or $-CH_2CH_2-$ to complete a 5- or 6-membered non-aromatic carbocyclic ring.

Patentansprüche

1. Donorelement für die thermische Übertragung mit einem Träger, der auf einer Seite eine in einem polymeren Bindemittel dispergierte fluoreszierende Diphenylpyrazolinverbindung aufweist und auf der anderen Seite des Trägers eine Gleitschicht mit einem Gleitmittel.

2. Element nach Anspruch 1, dadurch gekennzeichnet, daß die Verbindung der folgenden Formel entspricht:



worin bedeuten:

R Wasserstoff; Cyano; Carboxyalkyl; eine substituierte oder unsubstituierte Alkylgruppe mit 1 bis 6 Kohlenstoffatomen; eine substituierte oder unsubstituierte Arylgruppe mit 6 bis 10 Kohlenstoffatomen; und

J Wasserstoff; eine substituierte oder unsubstituierte Alkylgruppe mit 1 bis 6 Kohlenstoffatomen; eine substituierte oder unsubstituierte Arylgruppe mit 6 bis 10 Kohlenstoffatomen; oder $-CH_2-$ oder $-CH_2CH_2-$ zur Vervollständigung eines 5- oder 6-gliedrigen nicht-aromatischen carbocyclischen Ringes.

3. Element nach Anspruch 2, dadurch gekennzeichnet, daß J für Wasserstoff steht.

4. Element nach Anspruch 2, dadurch gekennzeichnet, daß R für Phenyl steht.


5. Element nach Anspruch 1, dadurch gekennzeichnet, daß das Donorelement in Folge wiederkehrende Einheiten von purpurrotem, gelbem und blaugrünem Farbstoff sowie der fluoreszierenden Verbindung aufweist.

6. Satz für die thermische Übertragung mit

a) einem Donorelement mit einem Träger, der auf einer Seite ein in einem polymeren Bindemittel dispergiertes Material und auf der anderen Seite des Trägers eine Gleitschicht mit einem Gleitmittel aufweist und
b) einem Empfangselement mit einem Träger, auf dem sich eine Bildempfangsschicht befindet,

wobei sich das Empfangselement in übereinander angeordneter Beziehung zum Donorelement befindet, so daß die Materialschicht in Kontakt mit der Bildempfangsschicht ist, dadurch gekennzeichnet, daß das Material eine fluoreszierende Diphenylpyrazolinverbindung ist.

7. Satz nach Anspruch 6, dadurch gekennzeichnet, daß die Verbindung der folgenden Formel entspricht:



worin bedeuten:


R Wasserstoff; Cyano; Carboxyalkyl; eine substituierte oder unsubstituierte Alkylgruppe mit 1 bis 6 Kohlenstoffatomen; eine substituierte oder unsubstituierte Arylgruppe mit 6 bis 10 Kohlenstoffatomen; und

J Wasserstoff; eine substituierte oder unsubstituierte Alkylgruppe mit 1 bis 6 Kohlenstoffatomen; eine substituierte oder unsubstituierte Arylgruppe mit 6 bis 10 Kohlenstoffatomen; oder $-CH_2-$ oder $-CH_2CH_2-$ zur Vervollständigung eines 5- oder 6-gliedrigen nicht-aromatischen Ringes.

Revendications

1. Élément donneur pour transfert thermique comprenant un support recouvert sur un de ses côtés par un composé fluorescent diphenylpyrazoline dispersé dans un liant polymère, et sur l'autre côté par une couche favorisant le glissement comprenant un lubrifiant.

2. Élément selon la revendication 1 caractérisé en ce que le composé a la formule :



où

R est un hydrogène, un groupe cyano, carboxyalkyle, un groupe alkyle substitué ou non de 1 à 6 atomes de carbone ; ou un groupe aryle substitué ou non de 6 à 10 atomes de carbone ; et

J est un hydrogène ; un groupe alkyle substitué ou non de 1 à 6 atomes de carbone ; un groupe aryle substitué ou non de 6 à 10 atomes de carbone ; ou peut représenter $-CH_2-$ ou $-CH_2CH_2-$ pour compléter un noyau carbocyclique non aromatique à 5 ou 6 chaînons.

3. Élément selon la revendication 2 caractérisé en ce que J est l'hydrogène.

4. Élément selon la revendication 2 caractérisé en ce que R est un groupe phényle.


5. Élément selon la revendication 1 caractérisé en ce que l'élément donneur comprend des séquences répétitives de zones de colorants magenta, jaune et cyan et le composé fluorescent.

6. Assemblage pour transfert thermique comprenant

a) un élément donneur de colorant comprenant un support recouvert sur un de ses côtés d'une couche contenant une substance dispersée dans un liant polymère et sur l'autre côté une couche favorisant le glissement comprenant un lubrifiant, et

b) un élément récepteur comprenant un support recouvert d'une couche réceptrice d'image, l'élément récepteur et l'élément donneur étant superposés de telle sorte que la couche contenant la substance est en contact avec la couche réceptrice d'image, caractérisé en ce que la substance est un composé fluorescent diphenylpyrazoline.

7. Assemblage selon la revendication 6 caractérisé en ce que le composé a la formule :



où

R est un hydrogène, un groupe cyano, carboxyalkyle, un groupe alkyle substitué ou non de 1 à 6 atomes de carbone ; ou un groupe aryle substitué ou non de 6 à 10 atomes de carbone ; et

J est un hydrogène ; un groupe alkyle substitué ou non de 1 à 6 atomes de carbone ; un groupe aryle substitué ou non de 6 à 10 atomes de carbone ; ou peut représenter $-CH_2-$ ou $-CH_2CH_2-$ pour compléter un noyau carbocyclique non aromatique à 5 ou 6 chaînons.